

Berkeley^{by} SFI Floors plank

specifications

Composition
ASTM F1700-96 C III – Type B
Minimum 67% Post-Consumer Recycled
Content by Weight

Static Load Limit
ASTM F970-93 – 1,500 p.s.i.

Wear Layer
0.15mm (7 mil) PVC with Polyurethane

Residual Indentation
KSM 3802 – 8%

Measurements

Tiles
17.9" x 17.9" x 0.12"
455mm x 455mm x 2mm
36.00 lbs./carton (22 tiles/carton)
52.29 ft²/carton

Slip Resistance
ASTM 1028 – Exceeds ADA
Wet/Dry Requirements for Level Surfaces

Heat Stability
KSM 3802 – 0.3mm (80° ± 2° C, 6 hrs/1 hr)

Radiant Heating
Suitable up to 28° C (85° F)

Wide Wood Planks
7.2" x 37.4" x 0.12"
184mm x 950mm x 2mm
37.50 lbs./carton (29 planks/carton)
52.64 ft²/carton

Specific Gravity
0.3/3.0 : 1.79
1.0/2.5 : 1.48

Narrow Wood Planks
3.6" x 37.4" x 0.12"
184mm x 950mm x 2mm
37.50 lbs./carton (58 planks/carton)
52.64 ft²/carton

Hardness
85-95 Shores (A-Type)

Castor Chair Suitability
Excellent

Perpendicularity
KSF 3802 - ±0.2mm

Flexibility
EN 345 (Method A: 20mm Mandrel Test) – Pass

Fire
ASTM E84 – 75 or less
ASTME648 – Class I
Mekel Burner Test – Pass

Chemical Resistance
Excellent

Smoke
ÖNORM B3800 – Q1

www.southlandfloors.com