

STARTER

Underlayment for
Laminate Floors

plus



Technical Data Sheet:

Property	Test Method	Performance
Gauge	Mm	1.5
Density	Lbs	2
Compressive Strength Vertical Direction (psi)	ASTM D3575-93 Suffix D @ 25% / 50%	3.0 11.5
Tensile Stress (psi) (@ Each Thickness)	ASTM D3575-93 Suffix T MD / CMD	68.0 25.0
Elongation (%)	ASTM D3575-93 Suffix T MD / CMD	19.0 8.5
Tear Resistance (lb/ft ³) (@ Each Thickness)	ASTM D3575-93 Suffix T MD / CMD	9.0 14.5
Density Range (lb/ft ³)	ASTM D3575-93	1.85 to 2.2
Water Vapor Transmission Rate GM / 100 in ² / 24 hr.	ASTM F-1249 Method 3005 FED STD 101	0.090 0.090

IMPORTANT NOTICE:

The above specifications were collected in a controlled environment. This information relates only to Easy Step and does not take into consideration the floor system and environment into which it will be used. Individual floor systems may affect the performance of Easy Step. Proper sub-floor preparations and following the finished floor manufacturer's instructions is crucial to a successful installation. Further information and about these tests are available.